

FINISHES

BASEMENTS	No additional paint finish is required.
INTERNAL WALLS	<ul style="list-style-type: none">• Direct paint; flat/texture.• Plasterboard and paint.
EXTERNAL WALLS	<ul style="list-style-type: none">• Direct paint; flat/texture.• Architectural textured polymer render finish.• Any form of cladding.• No applied finish (refer DCS website FAQ for finishes).

PAINT/RENDER WALL FINISHES

Common render finishes other than for architectural reasons are used by the industry to disguise the workmanship defects at a wall surface.

Dincel-Wall polymer thicknesses have been significantly increased to eliminate workmanship defects. Provided the recommendation of Dincel Construction System's Manual is adopted for the concrete placement, the installed surface of Dincel-Walls will be adequate to receive the following minimum finishes:

110 mm Walls Flat or texture paint finish.

200 mm Walls Texture paint finish.

This ability eliminates increased cost and time normally required for render finishes.



(200mm wall straightness several days after concrete fill)

DCS recommends using tested paint/render products from the following manufacturers only. The following is the general applied finish procedure for application to Dincel-Walls which should be confirmed by the chosen manufacturer.

- Step (1)** Clean surface, apply the appropriate primer by roller or airless spray.
- Step (2)** Apply a fine skim coat at the Dincel-Profile joints if the joints are required to be hidden for texture paint or fine render finishes. Alternatively, extend a fine skim coat to the entire wall surface for flat paint finishes.
- Step (3)** The third and final coat of finishes to consist of:
- (i) Top coat flat paint finish.
 - (ii) Textured paint finish.
 - (iii) Decorative/textured polymer (acrylic) render finish.

The texture/paint manufacturers listed below will offer warranty for the following statement.

The Texture/Paint products will not delaminate from DINCEL[®] - WALLS if applied as per the coatings manufacturer's specifications.

Company Name: **DULUX AUSTRALIA**

Contact Person's Name: Mr Warren Kelly

Phone: (02) 9794 9451 Fax: (02) 9794 9862 Email: warren.kelly@orica.com

Mobile: 0402 387 547 Website: www.acratex.com.au

Direct Link: http://www.dulux.com.au/media/604856/dincel_construction_system_acrylic_skimcoat_texture_system.pdf

Company Name: **PPG ARCHITECTURAL COATINGS**

Contact Person's Name: Mr Phil Rogers

Phone: (02) 9794 1200 Fax: (02) 9755 0425 Email: progers@ppg.com

Mobile: 0414 181 035 Website: www.taubmans.com.au

Direct Links: <http://www.specifi.com.au/Content/Specification/DCS01.pdf>
<http://www.specifi.com.au/Content/Specification/DCS02.pdf>
<http://www.specifi.com.au/Content/Specification/DCS03.pdf>
<http://www.specifi.com.au/Content/Specification/DCS04.pdf>

Company Name: **ROCKCOTE ENTERPRISES PTY LTD**

Contact Person's Name: Mr Rob Bennett

Phone: (02) 4978 6368 Fax: (02) 4940 8400 Email: rbennett@rockcote.com.au

Mobile: 0438 400 584 Website: www.rockcote.com.au

Company Name: **DECOMIX**

Contact Person's Name: Mr Mario Giusti

Email: info@decomix.com.au

Mobile: 0416 185 815

Website: www.decomix.com.au
